

Effect of alkalis on the Fe oxidation state and local environment in peralkaline rhyolitic glasses

Gabriele Giuli, Roberto Alonso-Mori, Maria Rita Cicconi, Eleonora Paris, Pieter Glatzel, Sigrid-Griet Eeckhout, Bruno Scaillet

► **To cite this version:**

Gabriele Giuli, Roberto Alonso-Mori, Maria Rita Cicconi, Eleonora Paris, Pieter Glatzel, et al.. Effect of alkalis on the Fe oxidation state and local environment in peralkaline rhyolitic glasses. *American Mineralogist*, Mineralogical Society of America, 2012, 97 (2-3), pp.468-475. 10.2138/am.2012.3888 . insu-00681280

HAL Id: insu-00681280

<https://hal-insu.archives-ouvertes.fr/insu-00681280>

Submitted on 21 May 2012

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

**Effect of alkalis on the Fe oxidation state and local environment in peralkaline rhyolitic
obsidians.**

Gabriele Giuli¹, Roberto Alonso Mori^{1,2‡}, Maria Rita Cicconi¹, Eleonora Paris¹, Pieter Glatzel², Sigrid Griet Eeckhout^{2,§}, and Bruno Scaillet³.

¹ School of Science and Technology, Geology Division, University of Camerino, Italy

² European Synchrotron Radiation Facility, Grenoble, France.

³ Inst. Sciences de la Terre d' Orleans, UMR6113 CNRS-UO, Orleans, France

Running title: Fe oxidation state in peralkaline rhyolitic glasses

Corresponding author: Gabriele Giuli

Tel. +39-0737-402606 FAX +39-0737-402644

e-mail: [**gabriele.giuli@unicam.it**](mailto:gabriele.giuli@unicam.it)

[‡] Current address: SLAC, Stanford University, USA.

[§] Current address: ONDRAF/NIRAS, Avenue des Arts 14, 1210 Brussels, Belgium.

ABSTRACT

Fe oxidation state and coordination geometry have been determined by Fe K-edge XANES (X-ray Absorption Near edge Spectroscopy) for three sets of silicate glasses of peralkaline rhyolitic composition with different peralkalinity values. These compositions have been chosen to investigate the effect of alkali content (and oxygen fugacity) on the Fe oxidation state. The samples have been produced by means of hydrothermal vessels at 800° C with oxygen fugacity conditions ranging from NNO-1.61 to NNO+2.96 log units.

Comparison of the pre-edge peak data with those of Fe model compounds with known oxidation state and coordination number allowed to determine the Fe oxidation state and coordination number in all the glasses analysed. Within each group of samples, Fe tends to oxidise with increasing oxygen fugacity as expected. However, alkali content is shown to have a strong effect on the $\text{Fe}^{3+}/(\text{Fe}^{3+}+\text{Fe}^{2+})$ ratio at constant oxygen fugacity: this ratio varies from 0.25 to 0.55 (± 0.05) for the least peralkaline series, and from 0.45 to 0.80 (± 0.05) for the most peralkaline series. Moreover, pre-edge peak data clearly indicate that Fe^{3+} is in [4] coordination in the most peralkaline glasses. Extrapolation of pre-edge peak data suggests the presence of both [4] and [5] coordination for trivalent Fe in the other two series. Divalent Fe is suggested to be mainly in [5] coordination in all the three glass series. The presence of minor amounts of [6] and [4] coordinated Fe cannot be ruled out by XANES data alone. XANES data suggest that the amount of alkalis also affects Fe^{3+} coordination environment decreasing the average coordination numbers.

EXAFS (Extended X-ray Absorption Fine Structure) data of the most oxidised and peralkaline sample indicate that Fe^{3+} is in tetrahedral coordination with $\langle \text{Fe-O} \rangle = 1.85\text{\AA}$ (± 0.02). This value compares well with literature data for $^{[4]}\text{Fe}^{3+}$ in crystalline phases (e.g. in

tetra-ferriphlogopite or rodolicoite) or in silicate glasses (e.g. phonolite glasses) supporting the XANES-determined coordination number obtained for the most peralkaline glasses.

Calculated NBO/T ratios decrease slightly with Fe oxidation because of the higher fraction of network forming Fe, thus increasing the polymerisation of the tetrahedral network.

Keywords: Iron local environment, rhyolitic glasses, EXAFS, XANES, alkalis

1. INTRODUCTION

Transition elements can affect glass/melts properties such as density, viscosity, and refraction index (see Mysen and Richet 2005). Moreover, their structural role in the melt affects their partition coefficients between melt and crystals in natural systems and is therefore important to understand the behaviour of minor to trace elements during crystallization. The knowledge of the control exerted by melt composition, P, T, and f_{O_2} conditions on the local structure of the transition elements is therefore of fundamental importance in relating the atomistic structure of silicate melts to their macroscopic properties. Despite the importance of these data, this is a topic where ample debate still exists and many studies and spectroscopic techniques have been employed in the aim of clarifying the structural role of transition elements.

Iron, the most common transition element in natural magmas, can exist in silicate melts in a variety of oxidation states and coordination numbers. Common Fe species in silicate melts and glasses include $^{[4]}\text{Fe}^{2+}$, $^{[5]}\text{Fe}^{2+}$, $^{[4]}\text{Fe}^{3+}$, and $^{[5]}\text{Fe}^{3+}$ (see Wilke et al. 2001, 2006; Rossano et al. 2000, 2008; Jackson et al. 1993, 2005; Giuli et al. 2002, 2005, 2008; Magnien et al., 2004); in few cases, also a minor presence of $^{[6]}\text{Fe}^{3+}$ (Wilke et al. 2004) and $^{[6]}\text{Fe}^{2+}$ (Calas and Petiau, 1983; Virgo and Mysen, 1985;) has been reported. Variation of the relative proportions of

these species implies variations in $\langle\text{Fe-O}\rangle$ distances and bond strengths, thus affecting glass/melt polymerisation, partial molar volumes of Fe species, melt density and viscosity. As varying oxygen fugacity affects the Fe oxidation state of a melt, oxygen fugacity can be expected to trigger considerable variations also in the viscosity of melts where Fe is a major element (Cukierman and Uhlman, 1974; Dingwell, 1991; Giuli et al. 2011; Dingwell et al. 2008).

More generally, Fe can affect considerably the melt structure and all related properties in silicate melts/magmas, when present in major amounts, in relation to a number of variables like P, T, oxygen fugacity, bulk melt composition. Alkali content is also known to affect Fe oxidation state in silicate melts (see Duffy 1992, 1996; Moretti and Ottonello, 2003 and references therein), but no measurements are available up to now to quantitatively assess to which extent alkalis can modify Fe structural role in glasses/melts. For this reason in this work we investigated the Fe structural role and oxidation state in three series of synthetic S-bearing rhyolite glasses characterised by different peralkalinity and produced in a range of different oxygen fugacity conditions to study the effect of the alkali content on the Fe oxidation state.

2. MATERIALS AND METHODS

The glasses were produced in the frame of a sulphur solubility study by Scaillet and McDonald (2006). Three compositions were chosen using well characterised peralkaline rhyolitic obsidians from the Naivasha area and the Kenya Rift Valley: two mildly peralkaline comendites (ND and SMN) and a pantalleritic obsidian (EBU). These compositions display a range of $(\text{Na}_2\text{O}+\text{K}_2\text{O})/\text{Al}_2\text{O}_3$ ratios (from 1.05, 1.31 to 1.88 for the ND, SMN and EBU respectively) and Fe contents (0.63, 2.11 and 4.96 total FeO for ND, SMN and EBU

respectively). Powdered glasses, mixed with 1 wt % S, were sealed in Au capsules and held at 800 °C 1.2 kbar in cold seal pressure vessels fitted with H₂ membrane. The fO₂ was varied with Ar-H₂ mixtures. More experimental details on the synthesis can be found in Scaillet and Mc Donald (2006). The compositions of the resulting glasses are reported in Table 1 in the form of weight percent oxide content. The Fe content (originally as total FeO) has been partitioned between FeO and Fe₂O₃ according to the XANES determined Fe³⁺/(Fe³⁺+Fe²⁺) ratio. The polymerisation of the tetrahedral network has been expressed as NBO/T ratio according to the procedure by Mysen and Richet (2005). In order to calculate the amount of tetrahedrally coordinated cations, Al and Si have been considered to be present as [4]-coordinated whereas Fe²⁺ as [5]-coordinated and Fe³⁺ as [4] and/or [5]-coordinated according to the XANES data of the samples.

Samples for absorption measurements were prepared as glass fragments embedded in resin with a finely polished surface. The standards used for XANES measurements are: a staurolite from Canton Ticino (Switzerland) and a synthetic Fe-akermanite for Fe²⁺ in tetrahedral coordination; a grandidierite from Madagascar for Fe²⁺ in trigonal dipyramidal coordination; a synthetic kirschsteinite, and a siderite from Erzberg (Austria) for Fe²⁺ in octahedral coordination; a natural andradite from Italy, and a natural aegirine from Malawi for Fe³⁺ in octahedral coordination; a natural yoderite from Mautia Hills (Tanzania) for Fe³⁺ in 5-fold coordination; a tetra-ferriphlogopite from Tapira (Brasil) for Fe³⁺ in 4-fold coordination (Giuli et al. 2001). The natural standards were separated by hand picking from thumb-sized crystals choosing the clearest portions to avoid impurities. All the standards were checked for purity by both optical microscopy and X-ray diffraction.

Model compounds for XAS measurement were prepared by smearing finely ground powder on a kapton tape, whereas the glass samples were prepared as slides with polished surfaces. The flat sample surface was placed at 45° from the X-ray beam directed towards the

fluorescence detector. Fe K-edge XANES spectra were recorded at room temperature at the ESRF on the undulator beamline ID26 (Gauthier et al. 1999, Solé et al. 1999) operating at 6 GeV in 16 bunch filling mode. A fixed-exit Si(311) double-crystal monochromator was used, providing an energy resolution of ~ 0.2 eV at the Fe K-edge. However, the main limitation for energy resolution is the finite core-hole width of the absorbing element (~ 1.15 eV at the Fe K-edge; Krause and Oliver 1979), resulting in a convoluted energy resolution (FWHM) of ~ 1.4 eV. The energy was calibrated by defining the first derivative peak of a metallic Fe reference foil to be at 7112.0 eV. Energy reproducibility has been tested by multiple collection some Fe model compound; the precision has been found to be within ± 0.05 eV or better. Two Si mirrors were used for the harmonics rejection of the incident X-ray beam. Beam dimension at the sample was 150x300 micrometers. XANES data were recorded in quick-scan mode by simultaneously scanning the monochromator angle and the undulator gap with a typical energy step of 0.1 eV and counting 44 ms per point. Each scan took 120 seconds and an average of 12 spectra was taken per sample. The spectra were acquired in fluorescence mode, using a Si photo-diode, and I_0 was monitored by measuring the fluorescence signal of a titanium foil using a Si photo-diode. The sample was positioned at 45° with respect to the beam and the detector.

3. DATA REDUCTION

Experimental XANES spectra were reduced by background subtraction with a linear function and then normalised for atomic absorption on the average absorption coefficient of the spectral region from 7170 to 7350 eV. The threshold energy was taken as the first maximum of the first derivative of the spectra, whereas peak positions were obtained by calculating the second derivative of the spectra. Pre-edge peak analysis was carried out

following the same procedure reported in Wilke et al. (2001), Farges (2001), and Giuli et al. (2002). The pre-edge peak region was analyzed by first subtracting an arctangent background from the normalised spectra and then by fitting the pre-edge peak by a sum of pseudo-Voigt functions. Pre-edge peak intensities along with energy positions were compared with those of the standards analysed here and others from the literature (e.g., Wilke et al. 2001; Farges 2001) in order to extract information on Fe oxidation state and coordination number in the glasses studied. Particular care was taken in using the smallest possible number of components in the pre-edge peak fitting procedure. In particular, the number (and, in some cases, the approximate energy) of the components was constrained to equal the number (and approximate energy) of the minima in the second derivative spectrum of the pre-edge peak. Several procedures have been tried for the pre-edge peak fitting: (1) simultaneous fitting of the background and the pseudo-Voigt component; (2) preliminary background subtraction followed by fitting with pseudo-Voigt component allowing the components to have different FWHM or Lorentian character; (3) preliminary background subtraction followed by fitting with pseudo-Voigt component constrained to have the same FWHM and Lorentian character. The third procedure produced the best results in terms of scatter of pre-edge peak integrated intensity and centroid energy (Giuli et al. 2011). In particular, reproducibility of the integrated intensity has been estimated to be within ± 0.002 by performing several fits to the background subtracted pre-edge peaks. Use of different procedures for arctangent background subtraction, however, can lead to higher errors in the integrated intensity, up to ± 0.035 .

The energy-intensity data of the fitted pre-edge peaks were compared with mixing lines calculated as intensity-weighted averages of 2 end-members: for divalent iron an ideal pre-edge peak has been chosen with integrated intensity equal to 0.11 and an energy 0.9 eV above the edge energy of metallic iron; for trivalent iron several possible pre-edge peak data have

been used in the calculation of mixing lines with integrated intensity ranging from 0.2 to 0.35 and with an energy 2.4 eV above the edge energy of metallic iron.

EXAFS data reduction and analysis was done by means of the GNXAS package (Filipponi and Di Cicco 2000). This program extracts the EXAFS signal ($\chi(k)$) from the raw spectrum without performing Fourier filtering and thus avoids possible bias derived from incorrect background subtraction. The theoretical amplitudes and phase shifts are calculated ab initio according to the muffin-tin approximation. The Hedin-Lundquist complex potential (Hedin and Lundquist 1971) was used for the exchange-correlation potential of the excited state. The amplitude reduction factor (S_0^2) has been fixed to 0.83, in agreement with the values observed for several crystalline standard and natural glasses (Giuli et al. 2002). This value is close to that used by Farges et al. (1994) of 0.82, and that used by Di Cicco et al. (1994) of 0.85.

4. RESULTS

4.1 XANES

Fe K-edge XANES spectra of the silicate glasses are shown in Figure 1a, 1b, and 1c arranged in order of increasing oxygen fugacity (ranging from NNO-1.61 to NNO+ 2.96 log units) from bottom to top. An evident increase of the edge energy is visible with increasing oxygen fugacity. Moreover, clear variations are visible in the edge region in the shape of the absorption maximum and in the intensity and energy position of the pre-edge peak P. These changes can be related to a variation in the Fe oxidation state and local structure.

This peak (P) is due to a *s-d* like electronic transition. Despite it is dipole-forbidden, it becomes partially allowed by mixing of the *d*-states of the transition metal with the *p*-states of

the surrounding oxygen atoms. This implies that the pre-edge peak energy position and intensity are greatly affected by the average Fe oxidation state and coordination geometry (Calas and Petiau 1983a, 1983b; Brown et al. 1995; Wilke et al. 2001). In particular, accurate evaluation of the pre-edge peak centroid energy and integrated intensity and comparison with those of Fe model compounds can provide quantitative information on both Fe oxidation state and coordination environment (see Wilke et al. 2001; Farges 2001; Giuli et al. 2002): its intensity will be minimal in case of regular octahedral symmetry (O_h) around the absorber, whereas it will reach its maximum in the case of tetrahedral coordination (T_d).

The background subtracted pre-edge peaks are shown in Figure 2a,b,c along with the pseudo-Voigt components and their sums, whereas their centroid energies and integrated intensity are reported in Table 2. Each pre-edge peak has been fitted with three components whose energies (ca. 7112.6, 7113.9, and 7114.5 eV) are fairly consistent with those of Fe model compounds. In particular, while the first and last components can be ascribed to contributions from Fe^{2+} and Fe^{3+} respectively, the component at intermediate energy results from contributions by both divalent and trivalent Fe. The relative importance of divalent or trivalent Fe causes an increase of the respective components resulting in an energy shift of the pre-edge peak centroid. The integrated intensity of the pre-edge peaks vs. their centroid energies are plotted in Figure 3 along with the data of Fe model compounds analysed here and elsewhere (Wilke et al. 2001; Farges 2001; Giuli et al. 2002). For the sake of simplicity, the relative energy is plotted (0 refers to the first maximum of the first derivative of metallic Fe spectrum) in order to avoid confusions when comparing data with literature data where a different edge energy value for metallic Fe has been chosen.

All divalent Fe model compounds plot at energies close to 0.9 eV above the metallic Fe edge, whereas trivalent Fe model compounds plot at energies close to 2.5 eV. At constant energy, the intensity of the model compounds pre-edge peaks varies according to the Fe

coordination geometry (the shaded ellipses refer to the range of coordination numbers in Fe model compounds).

In order to obtain quantitative data on Fe oxidation state and coordination number, mixing lines have been calculated between pre-edge peak intensity and energy values representative of possible Fe structural roles in silicate glasses (e.g. $^{[4]}\text{Fe}^{2+}$, $^{[5]}\text{Fe}^{2+}$, $^{[4]}\text{Fe}^{3+}$, $^{[5]}\text{Fe}^{3+}$, $^{[6]}\text{Fe}^{3+}$). All the pre-edge peak data are compatible with the presence of $^{[5]}\text{Fe}^{2+}$, $^{[4]}\text{Fe}^{3+}$ and $^{[5]}\text{Fe}^{3+}$; thus, in Figure 3 we show several mixing lines (dotted) between pre-edge peak values appropriate to these Fe species. The determined $\text{Fe}^{3+}/(\text{Fe}^{3+} + \text{Fe}^{2+})$ are then plotted in Fig. 4 as a function of experimental redox conditions.

The $\text{Fe}^{3+}/(\text{Fe}^{3+} + \text{Fe}^{2+})$ ratio varies systematically with oxygen fugacity within each series. For the ND series the $\text{Fe}^{3+}/(\text{Fe}^{3+} + \text{Fe}^{2+})$ ratio varies from 0.25 to 0.55 (± 0.05). However, increasing the alkali content strongly affects the Fe oxidation state: in fact, the $\text{Fe}^{3+}/(\text{Fe}^{3+} + \text{Fe}^{2+})$ ratio varies from 0.50 to 0.75 for the SMN series and from 0.45 to 0.80 for the EBU series.

In the same figure (Figure 3) it is shown that the silicate glasses data plot within three different region which form a trend of progressive oxidation. Despite every series has been synthesised in the same oxygen fugacity range, there is a clear shift to higher energy (i.e. to higher Fe oxidation states) with increasing (Na+K)/Al ratio (from 1.04 for ND to 1.31 for SMN and 1.81 for EBU). The trend observed in Figure 3 shows that, the higher is the alkali content, the higher the energy and intensity of the pre-edge peak. Despite the composition of the glasses is complex and involves changes also in the Fe content, this supports the idea that alkalis content strongly affects Fe oxidation state as well as Fe coordination number, producing more tetrahedral Fe^{3+} in the glass.

4.2 Fe coordination environment

The integrated intensities of the glasses pre-edge peaks can provide information on the average Fe coordination number and thus on the Fe coordination environment. The intensity chosen for divalent Fe to calculate the mixing lines is close to that of grandidierite, thus suggesting that divalent Fe is mostly five-fold coordinated in all these glasses. However, we must keep in mind that this result comes from extrapolating the pre-edge intensities of all glasses to lower energy and still represents a guess. Furthermore, it represents an average coordination number and, in principle, can be explained also by the presence of both $^{[4]}\text{Fe}^{2+}$, $^{[6]}\text{Fe}^{2+}$ or, alternatively, of $^{[4]}\text{Fe}^{2+}$, $^{[5]}\text{Fe}^{2+}$, and $^{[6]}\text{Fe}^{2+}$. However, experience on many natural and synthetic glasses (e.g. Giuli et al. 2002, 2003, 2005, 2008, 2011) for which both XANES and EXAFS data are available, suggests the presence of predominant $^{[4]}\text{Fe}^{2+}$ and $^{[5]}\text{Fe}^{2+}$, whereas only rarely is $^{[6]}\text{Fe}^{2+}$ found to be important; thus we propose that in the glasses studied here divalent Fe is present mainly in [5] (five-fold) coordination. On the other hand, trivalent Fe is clearly present in a different coordination environment. Comparison with mixing lines is consistent with higher pre-edge peak intensity of the trivalent Fe end-members when going from the ND to EBU series, thus suggesting a lower Fe^{3+} coordination number with increasing $(\text{Na}_2\text{O}+\text{K}_2\text{O})/\text{Al}_2\text{O}_3$ ratio. It must be noted that, despite the paucity of standards with four-fold and five-fold coordinated iron, there is sometimes a considerable scatter in the pre-edge peak integrated intensity of standards with the same coordination number and oxidation state, especially for tetracoordinated Fe^{2+} and Fe^{3+} . This scatter introduces a large error in the quantitative determination of the coordination number of our samples: while the pre-edge peaks of standards with $^{[5]}\text{Fe}^{2+}$ have integrated intensity at or very close to 0.1, the integrated intensity of the pre-edge peaks of standards with $^{[4]}\text{Fe}^{3+}$ range from 0.24 to 0.40 (see Table 2). Thus, depending on which standards are taken into consideration, the resulting average coordination number of the glasses examined can vary considerably. We tentatively suggest that trivalent Fe is found mainly in [4] coordination in the EBU series and

in a mixture of [4] and [5] coordination for the SMN and ND series. Should $^{61}\text{Fe}^{2+}$ or $^{61}\text{Fe}^{3+}$ be present in consistent amounts, the pre-edge peak intensity would be sensibly lower. However, their presence in minor amounts cannot be ruled out by XANES data alone. ~~It is worth remarking that~~ The fraction of tetrahedral Fe^{3+} increases at increasing alkali content

4.3 EXAFS

The experimental, theoretical and residual EXAFS signals of the EBU3 glass are shown in Figure 5a, whereas their Fourier transforms are shown in Figure 5b (see Table 3 with the essential parameters of the EXAFS fit). The EBU3 has been chosen for EXAFS analysis because it displays the highest $\text{Fe}^{3+}/(\text{Fe}^{3+}+\text{Fe}^{2+})$ ratio well in the field of $^{54}\text{Fe}^{3+}$, and it is therefore suitable to quantitatively determine the coordination environment of trivalent iron in these series.

Figure 5 shows that the fit is fairly satisfactory. Attempts to refine a distribution of different Fe-O distances did not improve the quality of the fit and resulted in convergence of the 2 or more theoretical signals to the same distance value. In the best fit of the EBU3 EXAFS spectrum, Fe was found to be tetrahedrally-coordinated ($N = 4 \pm 0.5$) with a $\langle \text{Fe-O} \rangle$ distance equal to $1.84 \text{ \AA} (\pm 0.02)$. This distance is close to that found in a $^{54}\text{Fe}^{3+}$ crystalline standard ($1.86 \text{ \AA} \pm 0.02$ for tetrahedrally coordinated Fe in tetra-ferriphlogopite; Giuli et al. 2001), and in other synthetic silicate glasses already characterised by XAS (Giuli et al. 2011) where trivalent Fe has been found to be in tetrahedral coordination and with similar bond distances ($1.85 \pm 0.01 \text{ \AA}$). Thus the data obtained by EXAFS analysis confirms the indications on the Fe coordination number derived from the XANES spectra of this sample.

5. DISCUSSION AND CONCLUSIONS

XANES spectra of three series of glasses produced in a range of oxygen fugacity display clear changes in the shape, edge energy position, pre-edge peak position and intensity which point out to major changes in the Fe oxidation state and coordination number as a function of both bulk melt composition and oxygen fugacity. The experimental pre-edge peak data form a gross trend going from values compatible with the presence of $^{[5]}\text{Fe}^{2+}$ species only to a region compatible with a mixture of $^{[4]}\text{Fe}^{3+}$, and $^{[5]}\text{Fe}^{3+}$ (see Figure 3), although the presence of minor $^{[6]}\text{Fe}^{2+}$ or $^{[6]}\text{Fe}^{3+}$ cannot be excluded from XAS data alone. The scatter of all the data points within the calculated mixing line indicates that the ratio between $^{[4]}\text{Fe}^{3+}$ and $^{[5]}\text{Fe}^{3+}$ species is not constant through all the oxygen fugacity conditions studied. Exact estimation of the ratio between $^{[4]}\text{Fe}^{3+}$ and $^{[5]}\text{Fe}^{3+}$ species is hindered by the wide range of pre-edge peak integrated intensities of Fe model compounds. However, it is reasonable to assume that the average coordination number of divalent Fe is [5] in all the samples, whereas trivalent Fe can be in [4] coordination in the EBU series and in a mixture of [4] and [5] coordination in the SMN and ND series. The observed decrease of the average Fe coordination number at increasing alkali content is in agreement with data from Spiering and Seifert (1985) and Iwamoto et al. (1978). However it should be noticed that, assuming that all the trivalent iron is tetrahedrally coordinated in the EBU series, whereas about half of the trivalent iron is tetrahedrally coordinated in the ND and SMN series, the ratio between the sum of alkalis and tetrahedral Al and Fe^{3+} is always greater than one [$\langle (\text{Na}+\text{K})/([\text{Al}]^{[4]}+\text{Fe}^{3+}) \rangle \sim 1.01, 1.26$ and 1.45 for the ND, SMN and EBU series respectively].

XANES determined $\text{Fe}^{3+}/(\text{Fe}^{2+}+\text{Fe}^{3+})$ ratio range from 0.25 to 0.55 (± 0.05) for the least peralkaline series (ND), from 0.51 to 0.75 (± 0.05) for the mildly peralkaline series (SMN), and from 0.45 to 0.80 (± 0.05) for the most peralkaline series (EBU). The effect of both oxygen fugacity conditions and alkali content on the Fe oxidation state can be clearly seen in Figure 5 for the three glass compositions. There is an evident net increase of the

$\text{Fe}^{3+}/(\text{Fe}^{3+}+\text{Fe}^{2+})$ ratio increasing the (Na+K)/Al value from 1.04 (ND) to 1.31 (SMN). On the other hand there is no marked variation as the (Na+K)/Al ratio is further increased from 1.31 to 1.81 (EBU). Within experimental error, the Fe oxidation states of the SMN and EBU series are very similar (Figure 5), however the EBU glasses display a sharp increase of the fraction of trivalent iron (from 0.52 to 0.69 ± 0.05) at f_{O_2} values ranging between -13 and -12.4. Moreover, the EBU series displays more tetrahedral Fe^{3+} than SMN as evidenced by the higher pre-edge peak intensity of the EBU samples (see Figure 3).

As a significant fraction of the trivalent iron is tetrahedrally coordinated in the studied glasses, in going from reducing to oxidising conditions there is an overall increase of the tetrahedrally coordinated (network forming) Fe, which leads to a slight increase of the overall glass polymerisation. The EBU series has the lowest NBO/T values (Table 1), because all trivalent Fe is tetrahedrally coordinated.

EXAFS data confirmed that trivalent Fe is tetrahedrally coordinated in the most peralkaline glasses. For the most oxidised sample (EBU3) the determined $\langle\text{Fe-O}\rangle$ distance ($=1.84 \pm 0.02 \text{ \AA}$) is compatible to that of tetrahedrally coordinated trivalent iron in rodolicoite (1.8255 \AA ; Arnold 1986) or in tetra-ferriphlogopite (1.86 \AA , Giuli et al. 2001). Also the refined coordination number is consistent with tetrahedral coordination (4 ± 0.5).

ACKNOWLEDGEMENTS

We wish to thank the staff of beam-line ID-26 (ESRF, F) for assistance during the XAS experiments. This research was supported by MIUR funds (Futuro in Ricerca 2008) to G.G.

REFERENCES

Brown, G.E., Farges, F., and Calas, G. (1995) X-ray scattering and X-ray spectroscopy studies of silicate melts. In: Stebbins J.F., McMillan P.F., Dingwell D. Eds., Structure, dynamics and properties of silicate melts. vol 32, 317-410. *Reviews in Mineralogy*, Mineralogical Society of America, Washington, D.C.

Calas, G., and Petiau, J. (1983a) Coordination of iron in oxide glasses through high-resolution K-edge spectra: information from the pre-edge. *Solid State Communications*, 48, 625-629.

Calas, G., and Petiau, J. (1983b) Structure of oxide glasses: Spectroscopic studies of local order and crystallochemistry. Geochemical implications. *Bulletin de Mineralogies*, 106, 33-55.

Cukierman, M., and Uhlmann, D.R. (1974) Effects of iron oxidation state on viscosity, Lunar composition 15555. *Journal of Geophysical Research*, 79, 1594-1598

Di Cicco, A., Berrettoni, M., Stizza, S., Bonetti, E., and Cocco, G. (1994) Microstructural defects in nanocrystalline iron probed by X-ray Absorption Spectroscopy. *Physics Review B*, 50, 17, 12386-12397.

Dingwell, D.B. (1991) Redox viscometry of some Fe-bearing silicate melts. *American Mineralogist*, 76, 1560-1562.

Dingwell, D.B., Hess, K.-U., and Valenti, P. (2008) Oxidation state dependence of viscosity in peralkaline lavas: Phonolite and Pantellerite. *American Geophysical Union, Fall Meeting 2008, Abstract V23G-2211*.

Duffy, J.A. (1992) A review of optical basicity and its applications to oxidic systems. *Geochimica et Cosmochimica Acta*, 57, 3961-3970.

Duffy, J.A. (1996) Redox equilibria in glass. *Journal of Non-Crystalline Solids*, 196, 45-50.

Farges, F. (2001). Crystal-chemistry of Fe in natural grandidierites: a XAFS spectroscopy study at the Fe K-edge. *Physics and Chemistry of Minerals*, 28, 619-629.

Farges, F., Guyot, F., Andrault, D., and Wang, Y. (1994) Local structure around Fe in $Mg_{0.9}Fe_{0.1}SiO_3$ perovskite: an X-ray absorption spectroscopic study at the Fe K-edge. *European Journal of Mineralogy*, 6, 303-312.

Filipponi, A. and Di Cicco, A. (2000) GNXAS: a software package for advanced EXAFS multiple-scattering calculations and data-analysis. *Task Quarterly*, 4, 575-669.

Gauthier, C., Solé, V.A., Signorato, R., Goulon, J. and Moguiline, E. (1999) The ESRF beamline ID26: X-ray absorption on ultra dilute sample. *Journal of Synchrotron Radiation*, 6, 164-166.

Giuli, G., Paris, E., Wu, Z., Brigatti, M.F., Cibin, G., Mottana, A., and Marcelli, A. (2001) Experimental and theoretical XANES and EXAFS study of tetra-ferriphlogopite. *European Journal of Mineralogy*, 13, 1099-1108.

Giuli, G., Pratesi, G., Paris, E., and Cipriani, C. (2002) Fe local structure in tektites and impactites by EXAFS and high-resolution XANES spectroscopy. *Geochimica et Cosmochimica Acta* 66: 4347-4353.

Giuli, G., Paris, E., Pratesi, G., Koeberl, C., and Cipriani C. (2003) Iron oxidation state in the Fe-rich layer and silica matrix of Libyan Desert Glass: a high resolution XANES study. *Meteoritics and Planetary Sciences*, 38, 1181-1186.

Giuli, G., Eeckhout, S.G., Paris, E., Koeberl, C., and Pratesi, G. (2005) Iron oxidation state in impact glass from the K/T boundary at Beloc, Haiti, by high-resolution XANES spectroscopy. *Meteoritics and Planetary Sciences*, 40, 1575-1580.

Giuli, G., Eeckhout, S. G., Koeberl, C., Pratesi, C., and Paris, E. (2008) Yellow impact glass from the K/T boundary at Beloc (Haiti): XANES determination of the Fe oxidation state and implications for formation conditions. *Meteoritics and Planetary Sciences*, 43, 981-986.

Giuli, G., Paris, E., Hess, K.U., Dingwell, D.B., Cicconi, M.R., Eckhout, S.G., Fehr, K.T., and Valenti, P. (2011) XAS determination of the Fe local environment and oxidation state in phonolite glasses and implications for the viscosity of silicate melts. *American Mineralogist*, 96, 631-636.

Jackson, W.E., Mustre de Leon, J., Brown, G.E., Jr., Waychunas, G.A., Conradsen, S.D., and Combes, J.M. (1993) High temperature XAS study of Fe₂SiO₄: Evidence for reduced coordination of ferrous iron in the liquid. *Science*, 262, 229-233

Jackson, W.E., Farges, F., Yeager, M., Mabrouk, P.A., Rossano, S., Waychunas, G.A., Solomon, E.I., and Brown, G.E. JR. (2005) Multi-spectroscopic study of Fe(II) in silicate glasses: Implications for the coordination environment of Fe(II) in silicate melts. *Geochimica et Cosmochimica Acta*, 69, 4315–4332

Hedin, L., and Lundquist, B.I. (1971) Explicit local exchange-correlation potentials. *Journal of Physics C* 4, 2064.

Iwamoto, N., Tsunawaki, Y., and Nakagawa, H. (1978) Investigation of Calcium-iron-silicate glasses by the Mössbauer method. *Journal of Non-Crystalline Solids*, 29, 347-356.

Keppler, H. (1992) Crystal Field spectra and geochemistry of transition metal ions in silicate melts and glasses. *American Mineralogist*, 77, 62-75.

Krause, M.O., and Oliver, J.H. (1979). Natural widths of atomic K and L levels, K alpha X-ray lines and several KLL auger lines. *Journal of Physical and Chemical Reference Data*, 8, 329-338.

Magnien, V., Neuville, D.R., Cormier, Mysen, B.O., Briois, V., Belin, S., Pinet, O., Richet, P. (2004) Kinetics of iron redox reactions in silicate melts: a preliminary XANES study. *Chemical Geology*, 213, 253-263.

Moretti, R., and Ottonello, G. (2003) Polymerization and disproportionation of iron and sulfur in silicate melts: insights from an optical basicity based approach. *Journal of Non-*

Crystalline Solids, 323, 111-119.

Mysen, B.O. and Richet, P. (2005) Silicate glasses and melts. Elsevier, Amsterdam, 545p.

Scaillet, B., and Mc Donald, R. (2006) Experimental and thermodynamic constrains on the sulphur yield of peralkaline and metaluminous silicic flood eruptions. *Journal of Petrology*, 47, 1413-1437.

Shannon, R.D., and Prewitt, C.T. (1970) Revised values of effective ionic radii. *Acta Crystallographica*, B25, 925-946.

Solé, A.V., Gauthier, C., Goulon, J., and Natali, F. (1999). Undulator QEXAFS at the ESRF beamline ID26. *Journal of Synchrotron Radiation*, 6, 174-175.

Spiering, B., Seifert, F. (1985) Iron in silicate glasses of granitic composition: a Mössbauer spectroscopic study. *Contribution to Mineralogy and Petrology*, 90, 63-73

Stahl, K., and Legres, J-P. (1990) On the crystal structure of staurolite. The X-ray crystal structure of staurolite from the Pirenees and Brittany. *Acta Crystallographica*, B 46, 292-301.

Wilke, M., Farges, F., Petit, P.E., Brown, G.E., and Martin, F. (2001). Oxidation state and coordination of Fe in minerals: an Fe K-XANES spectroscopic study. *American Mineralogist*, 86, 714-730.

Wilke, M., Partzsch, G.M., Bernhardt, R., Lattard, D. (2004). Determination of the iron oxidation state in basaltic glasses using XANES at the K-edge. *Chemical Geology* 213, 71-87.

Wilke, M., Schmidt, C., Farges, F., Malavergne, V., Gautron, L., Simionovici, A., Hahn, M., and Petit, P.E. (2006) Structural environment of Fe in water-bearing silicate glass and melt evidence from X-ray absorption spectroscopy. *Chemical Geology*, 229, 144-161.

Figure Captions

Fig.1:

(a,b,c) Experimental Fe K-edge XANES spectra of synthetic glasses under study. Spectra arranged from bottom to top in order of increasing oxygen fugacity. The spectra are normalised to unit intensity at the high energy side. Variations of the pre-edge peak (P) intensity and energy position are evident in passing from reducing to oxidising conditions. a) ND series; b) SMN series; c) EBU series.

Fig. 2:

Background subtracted pre-edge peaks of the studied glasses (empty circles) along with the pseudo-Voigt component used in the fitting procedures (dotted lines), and pseudo-Voigt sums (solid lines). Each pre-edge peak could be fitted with three components. All series have been plotted with the same vertical scale so as to enable direct comparison of the raw intensities. a) ND series; b) SMN series; c) EBU series.

Fig. 3:

Plot of the pre-edge peak integrated intensity vs. centroid energy position. Solid squares refer to the ND series, whereas red diamonds refer to the SMN series and blue circles refer to the EBU series. The small diamonds joined by the dotted lines represent mixing lines of pre-edge peaks calculated mixing between $^{[5]}\text{Fe}^{2+}$ with $^{[4]}\text{Fe}^{3+}$ and/or $^{[5]}\text{Fe}^{3+}$. It is evident the shift to higher energy and intensity of these samples with increasing peralkalinity.

Fig. 4:

Effect of alkali and oxygen fugacity on the Fe oxidation state for the three series of glasses. It can be clearly seen that there is a net increase of the $\text{Fe}^{3+}/(\text{Fe}^{3+}+\text{Fe}^{2+})$ ratio increasing the (Na+K)/Al ratio from 1.04 to 1.31. On the other hand there is no marked variation as the (Na+K)/Al ratio is further increased from 1.31 to 1.81.

Fig. 5

Comparison between the experimental, theoretical and residual Fe K-edge EXAFS signals of the EBU3 silicate glass. The EXAFS signals, in the energy range 7164.0 - 7650.0 eV are weighted by K^0 . Symbols as follows: circles, experimental; solid line, theoretical; dotted line, residual. (a) EXAFS signals (b) Fourier transforms. The disagreement index (Rfit) is 0.59E-05.

Table 1. Weight % oxide composition of the studied glasses (From Scaillet and Mc Donald 2006)

Sample	SiO ₂	Al ₂ O ₃	FeO ^a	Fe ₂ O ₃ ^a	CaO	MgO	K ₂ O	Na ₂ O	Cl	F	S	total	NBO/T ^b	(Na ₂ O+K ₂ O)/Al ₂ O ₃	(Na+K)/Al	Fe ³⁺ /Fe ^{tot c}
ND1	77.25	12.08	0.31	0.09	0.37	0.05	5.00	4.54	0.13	0.13	0.03	99.98	0.08	0.79	1.07	0.21
ND2	77.18	12.17	0.29	0.11	0.35	0.05	4.98	4.55	0.13	0.13	0.03	99.97	0.08	0.78	1.06	0.25
ND4	77.25	12.19	0.39	0.16	0.30	0.04	4.76	4.54	0.15	0.18	0.03	99.99	0.08	0.76	1.04	0.27
ND5	77.43	12.20	0.39	0.19	0.09	0.05	4.72	4.53	0.08	0.22	0.03	99.93	0.08	0.76	1.03	0.3
ND6	77.43	12.16	0.55	0.36	0.03	0.03	4.55	4.51	0.11	0.16	0.05	99.93	0.06	0.75	1.02	0.37
ND3	77.33	12.19	0.39	0.43	0.01	0.02	4.67	4.53	0.05	0.25	0.06	99.94	0.06	0.75	1.03	0.5
SMN1	75.60	10.67	1.03	1.20	0.06	0.02	4.45	5.71	0.26	1.07	0.02	102.20	0.14	0.95	1.33	0.51
SMN2	75.14	10.66	1.09	1.37	0.06	0.01	4.42	5.72	0.37	1.17	0.03	102.36	0.13	0.95	1.33	0.53
SMN4	75.23	10.75	0.86	1.78	0.03	0.01	4.33	5.70	0.22	1.20	0.04	102.60	0.12	0.93	1.31	0.65
SMN5	75.43	10.53	1.01	1.84	0.03	0.02	4.20	5.67	0.21	1.09	0.05	102.75	0.09	0.94	1.32	0.62
SMN6	76.51	10.73	0.52	1.18	0.01	0.00	4.24	5.65	0.08	1.08	0.05	101.63	0.08	0.92	1.29	0.67
SMN3	76.53	10.86	0.39	1.23	0.00	0.01	4.16	5.67	0.15	0.89	0.06	101.43	0.07	0.91	1.27	0.74
EBU1	74.09	8.30	2.85	2.60	0.23	0.01	4.41	6.52	0.35	0.79	0.07	100.22	0.03	1.32	1.87	0.45
EBU2	73.37	8.38	2.75	2.94	0.28	0.01	4.41	6.54	0.36	0.96	0.09	100.09	0.02	1.31	1.85	0.49
EBU4	73.75	8.29	2.65	3.20	0.14	0.01	4.19	6.50	0.23	0.82	0.09	99.87	0.02	1.29	1.84	0.52
EBU5	75.37	8.45	1.45	3.59	0.05	0.02	4.03	6.47	0.16	0.70	0.05	100.34	0.01	1.24	1.78	0.69
EBU6	75.65	8.46	1.20	3.59	0.02	0.02	4.05	6.46	0.12	0.66	0.04	100.27	0.01	1.24	1.77	0.73
EBU3	75.60	8.50	0.95	3.96	0.04	0.01	3.95	6.47	0.11	0.78	0.04	100.41	0.01	1.23	1.76	0.79

^a FeO and Fe₂O₃ have been recalculated from the original data taking into account XANES determined Fe³⁺/Fe^{tot} ratios.

^b Calculated assuming tetrahedral coordination for Si and Al and using XANES determined Fe oxidation states and coordination numbers (Fe³⁺ all tetrahedrally coordinated for the EBU series).

^c Determined by XANES comparing pre-edge peak data with those of Fe model compounds. Estimated error is ± 0.05

Table 2. Pre-edge peak data of the Fe K-edge XANES spectra

Sample name	Centroid (eV) ^a	Integrated intensity ^b	Fit agreement index (%)
Model compounds			
Siderite	7112.80	0.054	99.84
Kirschsteinite	7113.00	0.062	99.83
Grandidierite	7113.00	0.101	99.32
Staurolite	7113.00	0.218	99.88
Fe-Akermanite	7112.90	0.283	99.84
Andradite	7114.40	0.107	99.93
Aegirine	7114.51	0.103	99.97
Yoderite	7114.30	0.169	99.91
Tetra-ferriphlogopite	7114.53	0.401	99.97
Rhyolite glasses			
ND1	7113.46	0.135	99.92
ND2	7113.57	0.152	99.97
ND4	7113.60	0.150	99.97
ND5	7113.65	0.150	99.98
ND6	7113.71	0.152	99.94
ND3	7113.89	0.145	99.93
SMN1	7113.92	0.168	99.97
SMN2	7113.97	0.186	99.97
SMN4	7114.06	0.210	99.96
SMN5	7114.05	0.179	99.99
SMN6	7114.18	0.193	99.99
SMN3	7114.14	0.205	99.97
EBU1	7113.94	0.194	99.90
EBU2	7114.00	0.198	99.90
EBU4	7114.08	0.235	99.88
EBU5	7114.12	0.287	99.94
EBU6	7114.26	0.283	99.98
EBU3	7114.28	0.297	99.97

^a Energy reproducibility has been measured to be within ± 0.05 eV

^b reproducibility of the integrated intensity has been estimated to be within ± 0.002 by performing several fits to the background subtracted pre-edge peaks (see text).

Table 3: Essential parameters of the EXAFS fit.

$\langle \text{Fe-O} \rangle$ (Å)	1.84 (0.02)
σ^2 (Å ²)	0.0026
N	4.0 (0.5)
$\langle \text{Fe-Si} \rangle$ (Å)	3.40
σ^2 (Å ²)	0.018
$\langle \text{Fe-Na} \rangle$ (Å)	4.77
σ^2 (Å ²)	0.019
E_0 ref (eV)*	7123.20
E_0 exp (eV)*	7120.41
R fit	0.59E-05
S_0^2	0.83

* E_0 exp: experimental edge energy;

* E_0 ref: refined parameter for edge energy