^{17}O NMR evidence of free ionic clusters $\text{Mn}^{+}\text{CO}_3^{2-}$ in silicate glasses: Precursors for carbonate-silicate liquids immiscibility

Yann Morizet, Pierre Florian, Michael Paris, Fabrice Gaillard

► To cite this version:

Yann Morizet, Pierre Florian, Michael Paris, Fabrice Gaillard. ^{17}O NMR evidence of free ionic clusters $\text{Mn}^{+}\text{CO}_3^{2-}$ in silicate glasses: Precursors for carbonate-silicate liquids immiscibility. American Mineralogist, 2017, 102 (7), pp.1561-1564. 10.2138/am-2017-6133 . insu-01579409

HAL Id: insu-01579409

<https://hal-insu.archives-ouvertes.fr/insu-01579409>

Submitted on 2 Oct 2017

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Revision 1

**^{17}O NMR evidence of Free Ionic clusters $\text{M}^{n+} \cdot \text{CO}_3^{2-}$ in silicate glasses: Precursors for
carbonate-silicate liquids immiscibility**

Yann Morizet^{1*}, Pierre Florian², Michael Paris³, Fabrice Gaillard⁴

(1) Université de Nantes, Nantes Atlantique Universités, Laboratoire de Planétologie et
Géodynamique de Nantes (LPG), UMR CNRS 6112, 2 rue de la Houssinière, 44322
NANTES, France

(2) CNRS-CEMHTI Conditions Extrêmes et Matériaux: Haute Température et Irradiation,
UPR 3079, 1D avenue de la Recherche Scientifique, 45071, Orléans, France

(3) Institut des Matériaux Jean Rouxel (IMN), Université de Nantes, UMR CNRS 6502, 2 rue
de la Houssinière, BP32229, 44322 NANTES Cedex 3, France

(4) CNRS/INSU-Université d'Orléans – BRGM, UMR 7327, Institut des Sciences de la Terre
d'Orléans, 1A rue de la Férollerie, 45071, Orléans, France

Corresponding author: Yann Morizet

Postal address:

Laboratoire de Planétologie et Géodynamique de Nantes (LPG Nantes), UMR-CNRS 6112,
Université de Nantes.

2 rue de la Houssinière, 44322 Nantes Cedex (FRANCE)

phone: +33 (0) 2 5112 5491

fax: +33 (0) 2 5112 5268

*E-mail: yann.morizet@univ-nantes.fr

Abstract

Carbon dioxide is a ubiquitous component of low-silica melts such as kimberlites or melilitites. It is currently assumed that CO₂ molecules dissolving in low-silica melts as carbonate groups (CO₃²⁻) induce a strong polymerization of the silicate network; however, the exact molecular configuration of this dissolution mechanism is still debated.

Using ¹⁷O MAS NMR spectroscopy, we have investigated the carbonate molecular environment in a series of synthesized low-silica (31-41 wt.% SiO₂), CO₂-bearing (from 2.9 to 13.2 wt.% CO₂) silicate glasses analogous to melilitites and kimberlites. With the selective {¹³C}- {²⁷Al}- and {²⁹Si}-¹⁷O J HMQC NMR method, we show that CO₂ dissolved in the studied low-silica glasses is totally disconnected from the silicate network, forming Free Ionic Clusters (FIC) Mⁿ⁺..CO₃²⁻ with Mⁿ⁺ a charge compensating cation.

The Mⁿ⁺..CO₃²⁻ FIC are considered as precursors to immiscibility in between carbonate and silicate liquids. Observed in all studied compositions, we suggest that this immiscibility can be produced from moderately to strongly depolymerized silicate melt compositions.

INTRODUCTION

Providing constraints on the CO₂ dissolution mechanisms in depolymerized silicate melts contributes to our knowledge of kimberlite (Brooker et al. 2011; Russell et al. 2012), melilitite (Keller et al. 2006; Bosshard-Stadlin et al. 2014) and carbonatite genesis (Mitchell 2005), which are CO₂-enriched magmas. Carbonate – silicate liquid immiscibility is thought to be one possible genetic mechanism for these peculiar magmatic systems (Brooker and Kjarsgaard, 2011; Guzmics et al. 2015); however, the exact modalities of this mechanism remain poorly constrained.

Early work on CO₂ dissolution in silicate melt (Mysen et al. 1976; Eggler 1978; Mysen and Virgo 1980; Spera and Bergman 1980) suggested that CO₂ plays the role of polymerizing agent of the silicate network structure according to the following reaction:

In this reaction, a CO₂ molecule scavenges available oxygen from a Qⁿ (a SiO₄ tetrahedron unit with n bridging oxygen) unit to form a CO₃²⁻ group charge compensated by a network-modifying cation (e.g. Ca²⁺). Raman spectroscopic studies (Mysen et al. 2011; Mysen 2012; Moussallam et al. 2016) suggested that Eq. 1 proceeds to the right upon CO₂ dissolution inducing a change in the proportion of the different oxygen species (i.e. Non-Bridging Oxygen NBO and Bridging Oxygen BO). However, the exact molecular configuration of the CO₃²⁻ groups is not identified. Several dissolution mechanisms have been invoked for CO₂ molecules in silicate melts. It has been suggested that CO₂ can form network carbonates (T-CO₃²⁻-T with T = Si or Al) and NBO-CO₃²⁻ where a CO₂ molecule connects to an available NBO of a tetrahedron (Brooker et al. 2001; Guillot and Sator 2011; Morizet et al. 2014). An additional CO₂-dissolution mechanism has been proposed on the basis of molecular dynamic simulations (Xue and Kanzaki 2013; Vuilleumier et al. 2015) and also inferred from Raman spectroscopic studies (Mysen et al. 2011; Mysen 2012; Moussallam et al. 2016). In this mechanism the CO₃²⁻ molecular groups are present in the silicate network as Free Ionic Clusters Mⁿ⁺..CO₃²⁻ where Mⁿ⁺ is a charge balancing cation (i.e. alkali or alkaline-earth). Each type of CO₂-dissolution mechanism is a strong function of the glass chemical composition (Brooker et al. 2001). For a given chemical composition, the melt physical and chemical properties will be strongly affected by the type of CO₂-dissolution mechanism.

In the present work, we show direct proof of the Mⁿ⁺..CO₃²⁻ FIC existence in low-silica depolymerized melts. Based on ¹⁷O MAS NMR spectroscopy, we demonstrate that CO₃²⁻

69 molecular groups in low-silica melt are disconnected from the silicate network. Such a
70 dissolution mechanism represents the precursor of the immiscibility process between a silicate
71 melt and a carbonate melt.

72 EXPERIMENTAL METHOD

73 Several Fe-free glass compositions were investigated via ^{17}O NMR spectroscopy. The studied
74 compositions are depolymerized with SiO_2 content ranging from 30 to 40 wt.% (Table 1) and
75 a Non-Bridging Oxygen concentration per Tetrahedron (NBO/T) ratio of 1.2 to 3.2 calculated
76 from the chemical composition obtained from Electron Probe Micro-Analyses (EPMA, see
77 Table 1 and Supplementary material). Studied compositions are analogous to natural
78 kimberlites (Kjarsgaard et al. 2009) and melilitites (Keller et al. 2006).

79 The starting material was weighed into Pt capsules, which were then sealed by arc-welding.
80 Experiments were performed in piston-cylinder apparatus using $\frac{3}{4}$ inch talc-Pyrex high-
81 pressure assemblies between 0.5 and 1.5 GPa and at 1525°C. Details of the experimental
82 syntheses are provided in the Supplementary material.

83 ANALYTICAL METHOD

84 Major elements and CO_2 concentrations: EPMA and Raman spectroscopy

85 We performed micro-Raman analyses on a Jobin-Yvon LabRam 300 spectrometer equipped
86 with an Innova 300-5W Argon ion laser from Coherent© operating at a wavelength of 514 nm
87 to determine the CO_2 content dissolved in silicate glasses using the protocol proposed by
88 Morizet et al. (2013). A detailed description of the Raman analyses and the CO_2
89 determination from them is provided in Supplementary material.

90 NMR spectroscopy

91 All Solid State ^{17}O NMR were conducted on a Bruker 850 MHz Avance III Wide Bore
 92 spectrometer operating at a frequency of 115.3 MHz and referenced against liquid H_2O at 0
 93 ppm. The ^{17}O spectra were acquired using Full Hahn-echo and $\{^{27}\text{Al}, ^{13}\text{C}, ^{29}\text{Si}\}$ J-HMQC
 94 (Heteronuclear Multiple-Quantum Correlation) pulse sequences (Amoureux et al. 2007;
 95 Keeler 2010). The details of the analytical conditions are given in the Supplementary material.
 96 The J-HMQC experiment uses the so-called scalar coupling (“J”) which arises from the
 97 electrons involved in the bond between two nuclei and allows the creation of Heteronuclear
 98 Multiple-Quantum Coherences. In an $\{X\}$ - ^{17}O J-HMQC experiment where oxygen is the
 99 observed nuclei and X the indirect one, the resulting ^{17}O spectrum displays only the oxygen
 100 environments that are chemically bound to X.

101 RESULTS AND DISCUSSION

102 The ^{17}O MAS and $\{X\}$ - ^{17}O J-HMQC NMR spectra are shown in Figure 1 for several samples:
 103 XE-2 (Figure 1A), HK-1 (Figure 1B), HK-M (Figure 1C) and RB8E-12 (Figure 1D). Several
 104 oxygen environments are witnessed in the ^{17}O MAS NMR spectra: $\sim +50$ ppm assigned to ^{17}O
 105 nuclei in BO configuration associated with Si or Al tetrahedra; $\sim +100$ ppm assigned to ^{17}O
 106 nuclei in NBO configuration (Stebbins et al. 1999; Lee and Stebbins 2003; Kelsey et al. 2008)
 107 and $\sim +160$ ppm assigned to ^{17}O nuclei in CO_3^{2-} environments (Morizet et al. 2017). The peak
 108 at $\sim +100$ ppm is less apparent in Mg-bearing compositions (HK and XE) whereas it is
 109 prominent in Mg-free Ca-rich RB8E composition consistent with the peak assignment to Ca^{2+}
 110 NBO (Thompson and Stebbins 2011). The presence of Mg^{2+} surrounded by oxygen atoms
 111 units is proposed at $\sim +50$ -70 ppm (Allwardt and Stebbins 2004) but not clearly visible here
 112 due to strong overlap with the BO-(Si,Al) signal at $\sim +50$ ppm.
 113 The selective heteronuclear $\{X\}$ - ^{17}O J-HMQC NMR pulse sequence probes local
 114 environments of oxygen atoms bound to X atoms. Hence, it should be pointed out that

chemical bonds involving nuclei other than the considered one (X) will not contribute to the ^{17}O NMR signal in the $\{\text{X}\}$ - ^{17}O J-HMQC spectrum. Serendipitously, the $\{^{13}\text{C}\}$ - ^{17}O J-HMQC spectra show a single line located at $\sim +160$ ppm confirming that this peak is associated with CO_3^{2-} molecular groups. More importantly, the absence of signal at $\sim +50$ or $+100$ ppm indicates that the CO_3^{2-} is connected neither to an available NBO nor to a BO. This is also confirmed by the $\{^{29}\text{Si}\}$ - ^{17}O J-HMQC spectra, which do not exhibit a signal at $+160$ ppm but only at $+50$ and $+100$ ppm; this is consistent with ^{17}O atoms in BO and NBO configuration, respectively. The absence of common ^{17}O signals in the $\{^{29}\text{Si}\}$ - ^{17}O J-HMQC and $\{^{13}\text{C}\}$ - ^{17}O J-HMQC spectra shows that there is no oxygen atom simultaneously bound to silicon and carbon atoms (within the detection level of $\sim 5\%$) thereby precluding the existence of T- CO_3^{2-} -T and NBO- CO_3^{2-} carbonate units. This CO_2 -dissolution mechanism has been proposed on the basis of FTIR results (Brooker et al. 2001), inferred from Molecular Dynamic simulations (Vuilleumier et al. 2015) and indirectly suggested from the change in the network structure upon CO_2 -dissolution (Mysen et al. 2011; Mysen 2012; Moussallam et al. 2016). Our results are consistent with the MD results from Vuilleumier et al. (2015) suggesting that FIC represents 75% of the dissolved CO_3^{2-} molecular groups and 25% corresponding to network carbonate units (T- CO_3^{2-} -T with T = Si or Al; Brooker et al. 2001). In the FIC $\text{M}^{n+}.. \text{CO}_3^{2-}$, M^{n+} is a charge balancing cation which can be Mg^{2+} , Ca^{2+} and Na^+ to a lower extent (Na_2O is ~ 5 wt.%) for the currently investigated compositions. Although, Morizet et al. (2017) showed that CO_3^{2-} groups dissolve preferentially in the vicinity of Ca^{2+} cations, we do not exclude the possibility for $\text{Mg}^{2+}.. \text{CO}_3^{2-}$ being formed considering that Mg^{2+} could play a role comparable to Ca^{2+} (Cormier and Cuello 2013).

At this point, we wish to raise the level of confidence in the above discussion. Indeed, one could argue that the ^{17}O signal from Si-O-C linkages could be absent from the $\{^{29}\text{Si}\}$ - ^{17}O J-HMQC spectrum if the associated $J(^{29}\text{Si}-^{17}\text{O})$ coupling value strongly differs from those

occurring for ^{29}Si - $^{17}\text{O}(\text{BO})$ or ^{29}Si - $^{17}\text{O}(\text{NBO})$ linkages. A simple way to rule out this possibility is to show that the full ^{17}O spectrum can be totally reconstructed as the sum of the 3 selective $\{\text{X}\}$ - ^{17}O J-HMQC spectra. The reconstructions of the ^{17}O MAS NMR spectra from the deconvolution of the $\{\text{X}\}$ - ^{17}O J-HMQC spectra are shown in Figure 2 for three ^{17}O MAS NMR spectra: Mg-free RB8E-12 (Figure 2A) and Mg-bearing XE-2 and HK-1 (Figure 2B and C). The deconvolution procedure was conducted as follows: each $\{\text{X}\}$ - ^{17}O J-HMQC NMR spectrum was fitted with Gaussian lines; one line for the $\{^{13}\text{C}\}$ - ^{17}O J-HMQC, one line for the $\{^{27}\text{Al}\}$ - ^{17}O J-HMQC and two lines for the $\{^{29}\text{Si}\}$ - ^{17}O J-HMQC corresponding to the BO-Si and NBO-Si environments, respectively. The parameters obtained are reported in Table 1. Since the $\{^{27}\text{Al}\}$ - ^{17}O J-HMQC spectrum was not acquired for all the samples due to the requirement of very long acquisition times, we used the δ_{iso} and FWHM from the XE-2 deconvolution for HK spectra; and the average δ_{iso} and FWHM obtained from RB8E-12 and RB8E-13 for RB8E-7 spectrum. In Figure 2A, we show that the performed deconvolution adequately reproduces the ^{17}O MAS NMR spectrum for the Mg-free RB8E-12 sample. The high carbon content of this sample excludes the possibility of a lack of ^{17}O signal of significant intensity in the $\{^{29}\text{Si}\}$ - ^{17}O J-HMQC spectrum. For Mg-bearing compositions, the ^{17}O MAS NMR spectra are not perfectly reproduced by the deconvolution. Regardless of the glass composition (XE-2 and HK), the residuals of the simulation exhibit a signal located at $\sim +70$ ppm not accounted for. Considering that this residual NMR signal is only observed in Mg-bearing glass composition, the signal could be attributed to oxygen atoms in MgO_x configuration. This assignment would be consistent with the results of Hung et al. (2016) which identified ^{17}O resonance for MgO_x oxygens in Ca/Mg orthosilicate glasses at $+60$ ppm. Considering that the NMR signal of the CO_3^{2-} environments is reproduced adequately by a single line at $\sim +160$ ppm, the majority of the CO_3^{2-} groups are FIC in the investigated glass compositions.

IMPLICATION FOR CARBONATE – SILICATE LIQUID IMMISCIBILITY

Numerous implications arise from the present results; however we only focus on two of them:

1) the immiscibility between carbonate and silicate liquids and 2) the impact of FIC on the carbonated melt transport properties. It is reasonable to consider that the $M^{n+}..CO_3^{2-}$ FIC constitutes a carbonate subnetwork intimately mixed within a silicate subnetwork. For instance, Kubicki and Stolper (1995) showed that the molecular energy involved for ion pairs complexes (similar to FIC $M^{n+}..CO_3^{2-}$) is low as compared to any other type of carbonates dissolved in silicate melt. Therefore, the energy barrier to dissociate the carbonate subnetwork from the silicate subnetwork is lower in the case of FIC.

Network-modifying cations have varying coordination numbers in a silicate melt (e.g. 5 to 8 for Ca^{2+} ; Cormier and Cuello 2013). Upon CO_2 dissolution, the network-modifying cation will share less of its positive charges to the silicate network in order to compensate the negative charges of the CO_3^{2-} groups; resulting in a network-modifying cation that is less connected to the silicate network. In particular, Vuilleumier et al. (2014) showed that the Ca-O distance in molten $CaCO_3$ is on average 2.35 Å, suggesting that Ca^{2+} is more closely connected to the carbonate subnetwork than to the silicate subnetwork. Consequently, we believe that the presence of FIC $M^{n+}..CO_3^{2-}$ could be viewed as a possible precursor to immiscibility. For instance, removal of the carbonate network from the silicate network is a proposed mechanism to form calciocarbonatite from a melilitite parental melt (Guzmics et al. 2015).

We suggest that this immiscibility could also proceed from kimberlite owing to the fact that FIC groups are observed in the investigated HK composition analogous to kimberlite melt. However, the molecular configuration $M^{n+}..CO_3^{2-}$ FIC poses the problem of the way CO_2 degasses from depolymerized silicate melts. The CO_2 migration into the fluid phase imposes a

189 molecular structure reconfiguration to dissociate the $M^{n+}..CO_3^{2-}$ groups and causes the
190 network-modifying cation to remain in the silicate melt, thus depolymerizing the silicate
191 network structure. This difficulty could explain the absence of degassing in kimberlitic melt
192 upon decompression as witnessed by Moussallam et al. (2015).

193 Finally, it turns out that the identified CO_2 -dissolution mechanism can also affect the physical
194 properties of carbonated melts (e.g. magma transport and electrical conductivity).

195 Interconnection between FIC molecular groups could explain the high electrical conductivity
196 observed in CO_2 -bearing silicate melt (Sifré et al. 2014). There is an intimate mixture between
197 a carbonate subnetwork having an extremely low viscosity and a silicate subnetwork with a
198 higher viscosity (Morizet et al. *in press*). Through immiscibility, the carbonate liquid will
199 migrate towards the surface due to its low viscosity and density (Vuilleumier et al. 2014),
200 whereas the silicate liquid, which becomes enriched in SiO_2 , is stalled at depth due to the
201 increased viscosity (Giordano et al. 2008). Therefore, the direct proof of the existence of FIC
202 gives legitimacy to the development and application of the immiscibility theory in a wide
203 range of processes taking place in the Earth's interior.

204 *Acknowledgement: The authors thank the ANR agency which financed the current work*
205 *through the ANR-2010-BLAN-621 "Electrolith". The authors would like to thank the*
206 *European Research Council who partly funded this work through the ERC project grant*
207 *number 279790. The authors thank the University of Orléans, the University of Nantes and*
208 *the CNRS for their access to analytical facilities. The authors thank the TGIR RMN Très*
209 *Hauts Champs for accessing to the high field NMR spectrometer.*

210

211 References

212 Allwardt, J.R., and Stebbins, J.F. (2004) Ca-Mg and K-Mg mixing around non-bridging O
213 atoms in silicate glasses: an investigation using ^{17}O MAS and 3QMAS NMR. American
214 Mineralogist 89, 777–784.

215 Allwardt, J.R., Lee, S.K., and Stebbins, J.F. (2003) Ca-Mg and K-Mg mixing around non-
 216 bridging O atoms in silicate glasses: An investigation using ^{17}O MAS and 3QMAS NMR.
 217 American Mineralogist 89, 777-784.

218 Amoureux, J.P., Trebosc, J., Wiench, J., and Pruski, M. (2007) HMQC and refocused-INEPT
 219 experiments involving half-integer quadrupolar nuclei in solids. Journal of Magnetic
 220 Resonance 184, 1-14. Bosshard-Stadlin, S.A., Mattsson, H.B., and Keller, J. (2014) Magma
 221 mixing and forced exsolution of CO_2 during the explosive 2007–2008 eruption of Oldoinyo
 222 Lengai (Tanzania). Journal of Volcanology and Geothermal Research 285, 229–246.

223 Brooker, R.A., and Kjarsgaard, B.A. (2011) Silicate–carbonate liquid immiscibility and phase
 224 relations in the system $\text{SiO}_2\text{--Na}_2\text{O--Al}_2\text{O}_3\text{--CaO--CO}_2$ at 0.1–2.5 GPa with applications to
 225 carbonatite genesis. Journal of Petrology 52, 1281–1305.

226 Brooker, R.A., Kohn, S.C., Holloway, J.R., and McMillan, P.F. (2001) Structural controls on
 227 the solubility of CO_2 in silicate melts. Part II: IR characteristics of carbonate groups in silicate
 228 glasses. Chemical Geology 174, 241–254.

229 Brooker, R.A., Sparks, R.S.J., Kavanagh, J.L., and Field, M. (2011) The volatile content of
 230 hypabyssal kimberlite magmas: some constraints from experiments on natural rock
 231 compositions. Bulletin of Volcanology, 73, 959–981.

232 Cormier, L., and Cuello, G.J. (2013) Structural investigation of glasses along the $\text{MgSiO}_3\text{--}$
 233 CaSiO_3 join: Diffraction studies. Geochimica et Cosmochimica Acta 122, 498-510.

234 Eggler, D.H. (1978) The effect of CO_2 upon partial melting of peridotite in the system $\text{Na}_2\text{O--}$
 235 $\text{CaO--Al}_2\text{O}_3\text{--MgO--SiO}_2\text{--CO}_2$ to 35kb, with an analysis of melting in a peridotite- $\text{H}_2\text{O--CO}_2$
 236 system. American Journal of Science 278, 305–343.

- 237 Giordano, D., Russell, J.K., and Dingwell, D.B. (2008) Viscosity of magmatic liquids: a
238 model. *Earth Planetary Science Letters* 271, 123–134.
- 239 Guillot, B., and Sator, N. (2011) Carbon dioxide in silicate melts: A molecular dynamics
240 simulation study. *Geochimica et Cosmochimica Acta* 75, 1829-1857.
- 241 Guzmics, T., Zajacz, Z., Mitchell, R.H., Szabo, C., and Wälle, M. (2015) The role of liquid–
242 liquid immiscibility and crystal fractionation in the genesis of carbonatite magmas: insights
243 from Kerimasi melt inclusions. *Contributions to Mineralogy and Petrology* 169, 17-35.
- 244 Hung, I., Gan, Z., Gor'kov, P.L., Kaseman, D.C., Sen, S., LaComb, M., and Stebbins, J.F.
245 (2016) Detection of “free” oxide ions in low-silica Ca/Mg silicate glasses: Results from ^{17}O
246 $\rightarrow$ ^{29}Si HETCOR NMR. *Journal of Non-Crystalline Solids* 445-446, 1-6.
- 247 Keller, J., Zaitsev, A.N., and Wiedenmann, D. (2006) Primary magmas at Oldoinyo Lengai:
248 the role of olivine melilitites. *Lithos* 91,150–172
- 249 Keeler, J. (2010) *Understanding NMR Spectroscopy*. The Atrium, Chichester, West Sussex,
250 PO19 8SQ, United Kingdom, John Wiley & Sons Ltd., 526p.
- 251 Kelsey, K.E., Allwardt, J.R., and Stebbins, J.F. (2008) Ca-Mg mixing in aluminosilicate
252 glasses: An investigation using the ^{17}O MAS and 3QMAS and ^{27}Al MAS NMR. *Journal of*
253 *Non-Crystalline Solids* 354, 4644–4653.
- 254 Kjarsgaard, B.A., Pearson, D.G., Tappe, S., Nowell, G.M., and Dowall, D.P. (2009)
255 Geochemistry of hypabyssal kimberlites from Lac de Gras, Canada: Comparisons to a global
256 database and applications to the parent magma problem. *Lithos* 1125, 236-248.

- 257 Kubicki, J.D., and Stolper, E.M. (1995) Structural roles of CO₂ and [CO₃]²⁻ in fully
 258 polymerized sodium aluminosilicate melts and glasses. *Geochimica et Cosmochimica Acta*
 259 59, 683-698.
- 260 Le Bas, M.J. (1987) Nephelinites and carbonatites. Geological Society Special Publication 30,
 261 53-83.
- 262 Lee, S.K., and Stebbins, J.F. (2003) Nature of cation mixing and ordering in Na-Ca silicate
 263 glasses and melts. *Journal of Physical Chemistry B* 107, 3141–3148.
- 264 Mitchell, R.H. (2005) Carbonatites and carbonatites and carbonatites. *Canadian Mineralogist*
 265 43, 2049–2068.
- 266 Morizet, Y., Brooker, R.A., Iacono-Marziano, G., and Kjarsgaard, B. (2013) Quantification of
 267 CO₂ dissolved in silicate glasses of various compositions with Micro-Raman spectroscopy.
 268 *American Mineralogist* 98, 1788–1802.
- 269 Morizet, Y., Paris, M., Gaillard, F., and Scaillet, B. (2014) Carbon dioxide in silica-
 270 undersaturated melt. Part I: the effect of mixed alkalis (K and Na) on CO₂ solubility and
 271 speciation. *Geochimica et Cosmochimica Acta* 141, 45–61.
- 272 Morizet, Y., Paris, M., Sifré, D., Di Carlo, I., and Gaillard, F. (2017) The effect of Mg
 273 concentration in silicate glasses on CO₂ solubility and solution mechanism: Implication for
 274 natural magmatic systems. *Geochimica et Cosmochimica Acta* 198, 115-130.
- 275 Morizet, Y., Paris, M., Sifré, D., Di Carlo, I., Ory, S., and Gaillard, F. (*in press*) Towards the
 276 reconciliation of viscosity change and CO₂-induced polymerization in silicate melts. *Chemical*
 277 *Geology* DOI: 10.1016/j.chemgeo.2017.03.028.

- 278 Moussallam, Y., Morizet, Y., Massuyeau, M., Laumonier, M., and Gaillard, F. (2015) CO₂
 279 solubility in kimberlite melts. *Chemical Geology* 418, 198-205.
- 280 Moussallam, Y., Florian, P., Corradini, D., Morizet, Y., Sator, N., Vuilleumier, R., Guillot,
 281 B., Iacono-Marziano, G., Schmidt, B.C., and Gaillard, F. (2016) The molecular structure of
 282 melts along the carbonatite–kimberlite–basalt compositional joint: CO₂ and polymerization.
 283 *Earth Planetary Science Letters* 434, 129-140.
- 284 Mysen, B.O. (2012) Silicate-COH melt and fluid structure, their physicochemical properties,
 285 and partitioning of nominally refractory oxides between melts and fluids. *Lithos* 148, 228-
 286 246.
- 287 Mysen, B.O., and Virgo, D. (1980) Solubility mechanisms of carbon dioxide in silicate melts;
 288 a Raman spectroscopic study. *American Mineralogist* 65, 885–899.
- 289 Mysen, B.O., Eggler, D.H., Setiz, M.G., and Holloway, J.R. (1976) Carbon dioxide in silicate
 290 melt and crystals: Part I solubility measurements. *American Journal of Science* 276, 455-479.
- 291 Mysen, B.O., Kumamoto, K., Cody, G.D., and Fogel, M.L. (2011) Solubility and solution
 292 mechanisms of C-O-H volatiles in silicate melt with variable redox conditions and melt
 293 composition at upper mantle temperatures and pressures. *Geochimica et Cosmochimica Acta*
 294 75, 6183–6199.
- 295 Russell, J.K., Porritt, L.A., Lavallée, Y., and Dingwell, D.B. (2012) Kimberlite ascent by
 296 assimilation-fuelled buoyancy. *Nature* 481, 352–356.
- 297 Sifré, D., Gardès, E., Massuyeau, M., Hashim, L., Hier-Majumder, S., and Gaillard, F. (2014)
 298 Electrical conductivity during incipient melting in the oceanic low-velocity zone. *Nature* 509,
 299 81–87.

- 300 Spera, F.J., and Bergman, S.C. (1980) Carbon dioxide in igneous petrogenesis: I. Aspects of
 301 the dissolution of CO₂ in silicate liquids. *Contributions to Mineralogy and Petrology* 74, 55-
 302 66.
- 303 Stebbins, J.F., Lee, S.K., and Oglesby, J.V. (1999) Al-O-Al oxygen sites in crystalline
 304 aluminates and aluminosilicate glasses: high-resolution oxygen-17 NMR results. *American*
 305 *Mineralogist*, 84, 983–986.
- 306 Thompson, L.M., and Stebbins, J.F. (2011) Non-bridging oxygen and high-coordinated
 307 aluminum in metaluminous and peraluminous calcium and potassium aluminosilicate glasses:
 308 High-resolution ¹⁷O and ²⁷Al MAS NMR results. *American Mineralogist* 96, 841–853.
- 309 Vuilleumier, R., Seitsonen, A., Sator, N., and Guillot, B. (2014) Structure, equation of state
 310 and transport properties of molten calcium carbonate (CaCO₃) by atomistic simulations.
 311 *Geochimica et Cosmochimica Acta* 141, 547-566.
- 312 Vuilleumier, R., Seitsonen, A.P., Sator, N., and Guillot, N. (2015) Carbon dioxide in silicate
 313 melts at upper mantle conditions: Insights from atomistic simulations. *Chemical Geology* 418,
 314 77–88.
- 315 Xue, X., and Kanzaki, M. (2013) Carbonate speciation in depolymerized silicate melts
 316 (glasses): New evidence from ab initio calculations and ¹³C MAS and static NMR
 317 measurements. *Mineralogical Magazine* 77, 2533.

318 **Figure caption:**

319 Figure 1. ¹⁷O MAS and {¹³C}- {²⁷Al}- {²⁹Si}- ¹⁷O J-HMQC NMR spectra of CO₂-
 320 bearing silicate glasses: XE-2 (A), HK-1 (B), HK-M (C) and RB8E-12 (D). Three oxygen
 321 environments are identified with MAS spectra: FIC Mⁿ⁺..CO₃²⁻, Ca²⁺ NBO-Si and BO-(Si,Al).
 322 The NMR spectra for the other synthesized glasses can be found in Supplementary material.

323 Figure 2. ^{17}O MAS spectrum deconvolution obtained from Gaussian lines derived
324 from $\{\text{X}\}$ - ^{17}O J-HMQC spectra. The deconvolution of the ^{17}O NMR spectra for the other
325 synthesized glasses can be found in Supplementary material.

Revision 1

Table 1: Experimental conditions, chemical compositions of the investigated synthetic Fe-free silicate glasses.

Sample	HK-1	HK-2	HK-M	RB8E-7	RB8E-12	RB8E-13	XE-2	Natural Kimberlite [§]	Natural Melilitite [§]
Pressure (GPa)	1.5	0.5	1.5	0.5	1.0	1.0	1.5		
Glass chemical composition in wt.%									
SiO ₂	40.2	40.1	31.8	33.3	30.3	30.1	40.6	30.4	36.5
Al ₂ O ₃	4.3	4.4	3.5	8.7	8.1	8.6	14.8	2.3	7.7
MgO	21.9	21.3	21.9	0.0	0.1	0.2	12.6	29.7	11.8
CaO	22.0	22.3	22.0	41.8	39.8	36.0	17.8	9.6	14.2
Na ₂ O	4.5	4.5	3.5	5.7	4.8	5.0	4.8	0.1	4.3
CO ₂ [*]	7.1	2.9	13.2	6.5	12.6	7.7	4.2	6.40	0.52
H ₂ O [†]	0.8	1.0	1.3	0.7	1.5	1.3	1.0	7.10	1.06
NBO/T from stoichiometry [‡]	2.6	2.5	3.2	2.1	2.2	1.9	1.2	3.60	1.66
NMR parameters									
Free Ca ²⁺ ..CO ₃ ²⁻									
δ _{iso}	154.2	157.3	155.7	164.9	164.6	166.0	157.8		
FWHM	42.0	41.3	44.2	34.7	30.7	33.6	45.3		
BO-Si									
δ _{iso}	54.4	57.4	55.2	61.0	51.6	53.4	48.7		
FWHM	24.4	29.3	24.3	23.3	24.3	22.3	25.5		
BO-Al									
δ _{iso}	42.5	42.5	42.5	47.8	45.5	47.5	42.5		
FWHM	25.8	25.8	25.8	25.6	25.7	25.5	25.8		
NBO-Si									
δ _{iso}	95.9	96.7	96.0	106.5	106.8	106.2	99.3		
FWHM	31.4	33.1	23.7	24.6	25.2	24.0	47.1		

^{*} The glass CO₂ content has been determined using Raman spectroscopy and the method described in Morizet et al. (2013). With the derived CO₃/HF ratio obtained from the deconvolution of the Raman spectra (see Supplementary material), it is possible to determine the CO₂ content using the linear relationship wt.% CO₂ = 13.5 x CO₃/HF. The typical error on the CO₂ content using Raman method is 10% in relative to the value.

[†] The H₂O content was determined by FTIR spectroscopy on a doubly polished glass plate. Contribution for OH⁻ and H₂O^{mol} vibrational peaks at 4500 and 5200 cm⁻¹ were summed to obtain the H₂O^{tot}. The error does not exceed ±0.2 wt.% H₂O and corresponds to the standard deviation obtained on the replicated measurements.

[‡] The NBO/T describing the average polymerization was calculated on a stoichiometric basis using the chemical composition measured by EPMA.

[§] An average typical natural composition of kimberlite and melilitite were obtained from Kjarsgaard et al. (2009) and Keller et al. (2006), respectively. Additional oxides (TiO₂, FeO and K₂O for the most important) have not been reported but are nominally present: ~0-4 wt.% for TiO₂, ~10.0 wt.% FeO and ~2.0 for K₂O.

Figure 1

Figure 2